

Abstract of the Disclosure

The present invention includes a method for preventing distortion in semiconductor fabrication. The method comprises providing a substrate comprising a film comprising silicon nitride. The substrate is treated in a vacuum of about 3.0-6.5 Torr in an atmosphere comprising oxygen plasma wherein the oxygen plasma flow rate is at least about 300 sccm oxygen. A resist is applied to the treated substrate and the resist is patterned over the treated substrate.

BEST AVAILABLE COPY

00258762-030400

"Express Mail" mailing label number: EM287849368US  
Date of Deposit: MARCH 1, 1999  
I hereby certify that this paper or fee is being deposited with the  
United States Postal Service "Express Mail Post Office to Addressee"  
service under 37 CFR 1.10 on the date indicated above and is  
addressed to the Assistant Commissioner for Patents,  
Washington, D.C. 20231  
Printed Name: CHRIS HAMMOND  
Signature: Chris Hammond